Ardex

FIBRE REINFORCED LEVELLING COMPOUND

ARDEX K 40HB

Outstanding flow and workability, even at 40mm.
Walk on after 2 hours, regardless of thickness.
Extended 35 minute working time
Fit LVT after 6 hours at 5mm

- Information ARDEX K 40HB

ARDEX K 40HB is a fibre reinforced, high build levelling and smoothing compound designed for applications from 3mm up to a maximum of 40mm.

ARDEX K 40HB hardens rapidly and can be walked on in as little as 2 hours, regardless of thickness, which means there's minimal disruption on live sites, particularly those that are constantly in use by the customer or other trades.

It has almost double the working time of competitor products, which means trowel marks drop out with ease, joins between mixes can be easily spiked up to 35 minutes after application, and there's little or no additional preparation before fitting!

Applications up to 5mm can receive resilient floorcoverings, including timber, after 6 hours, and thicker applications up to 40mm after 48 hours. Ceramic floor tiles can be fixed 2 hours after application.

Apply most floorcoverings after 12 hours
Receives light foot traffic in as little as 2 hours
Excellent flow and application properties
Can be used on heated screeds

Unit Size Available: 22kg

Coverage: A 22kg bag of ARDEX K 40 HB will cover approximately 4m² at 3mm thick. Applications from 3mm up to a maximum of 40mm

- **Technical Data ARDEX K 40HB**

Compressive Strength
Greater than 30N/mm² at 28 days

Tensile Bedding Strength
Flexural Strength Greater than 8N/mm² at 28 days

Suitable for underfloor heating
Yes